



EMSL Analytical, Inc.

18369 Petroleum Drive Baton Rouge, LA 70809
Tel/Fax: (225) 755-1920 / (225) 755-1989
<http://www.EMSL.com> / batonrougelab@emsl.com

EMSL Order: 251802276
Customer ID: MATM50
Customer PO: 3857CAC
Project ID:


Attention: Paul Lo
MMG/Materials Management Group, Inc.
3520 General DeGaulle Drive
Suite 3010
New Orleans, LA 70114
Project: 3857CAC

Phone: (504) 368-0568
Fax: (504) 368-8409
Received Date: 04/25/2018 9:10 AM
Analysis Date: 04/25/2018
Collected Date: 04/24/2018

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
ROBA-11 <small>251802276-0001</small>	Mastic	Yellow Non-Fibrous Homogeneous		100% Non-fibrous (Other)	None Detected
ROBA-12 <small>251802276-0002</small>	Floor Filler	Yellow/Beige Non-Fibrous Heterogeneous		100% Non-fibrous (Other)	None Detected
ROBA-13-Cove Base <small>251802276-0003</small>	Baseboard & Glue	Black Non-Fibrous Homogeneous		100% Non-fibrous (Other)	None Detected
ROBA-13-Glue <small>251802276-0003A</small>	Baseboard & Glue	Yellow Non-Fibrous Homogeneous		100% Non-fibrous (Other)	None Detected
ROBA-14 <small>251802276-0004</small>	Mastic	Yellow Non-Fibrous Homogeneous		100% Non-fibrous (Other)	None Detected
ROBA-15 <small>251802276-0005</small>	Corkboard	Brown/Beige Fibrous Heterogeneous	70% Cellulose	30% Non-fibrous (Other)	None Detected
ROBA-16 <small>251802276-0006</small>	Corkboard Glue	Yellow Non-Fibrous Homogeneous		100% Non-fibrous (Other)	None Detected

Analyst(s)
Joshua Brunet (7)


Jamie Laginess, Laboratory Operations Manager
or Other Approved Signatory

EMSL maintains liability limited to cost of analysis. This report relates only to the samples reported and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Samples received in good condition unless otherwise noted. Estimated accuracy, precision and uncertainty data available upon request. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Reporting limit is 1%

Samples analyzed by EMSL Analytical, Inc. Baton Rouge, LA NVLAP Lab Code 200375-0, LELAP 01950, TX 300238

Initial report from: 04/25/2018 16:18:19